

TACTILE CLASSIC YELLOW URETHANE



TYPE	Tactile Ground Surface Indicator
RANGE	Warning Tactile
DESIGN	Classic
MATERIAL	UV stabilised thermo plastic urethane (TPU)
FINISH	Injection moulded
DIMENSIONS	OUTER DIA: 35mm TOP DIA: 25mm THICKNESS: 5mm



FEATURES

Injection moulded, concentric circle design on the horizontal face with a smooth outer edge

Complies with the NCC (D3.8 Tactile Indicators) and Disability (Access to Premises—Buildings) standards to meet the deemed-to-satisfy-provisions

Complies with slip resistance requirements as detailed in HB 198

Backed by 2 year warranty

Registered design

SLIP RESISTANCE TESTING

Important information: To determine a classification of a slip resistance rating, see Australian Standards Hand Book 198 (HB 198), a Guide to the specification and testing of slip resistance of pedestrian surfaces. This document outlines the minimum ratings of a location and situation of a pedestrian surface.

TEST AS 4586 APPENDIX A: Wet Pendulum Test

FOUR S 96 SLIDER = 75 **CLASS** = P5

TRL 55 SLIDER = 73 **CLASS** = P5

TEST AS 4586 APPENDIX C: Wet/Barefoot Ramp Test

MEAN ANGLE OF INCLINATION = 27° **CLASS** = C

TEST AS 4586 APPENDIX D: Oil/Wet Ramp Test

CORRECTED MEAN OVERALL ACCEPTANCE ANGLE = 24° **CLASS** = R11

LUMINANCE TESTING

Important information: To determine a luminance contrast between a substrate and the DTAC TGSi, see: AS/NZS 1428.4.1:2009. DTAC can test your substrate for luminance contrast to give you peace of mind that your DTAC project will be fully compliant to AS/NZS 1428.4.1 Appendix E.

TEST AS/NZS 1428.4.1 APPENDIX E PARAGRAPH E3

LUMINANCE REFLECTANCE RATING / WET = 65.95

LUMINANCE REFLECTANCE RATING / DRY = 66.34

FIRE TESTING

Important information: The results displayed in this document relate to the behaviour and environment of the product in the conditions to which the test was carried out. This is not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

TEST AS/ISO 9239.1: Reaction to Fire Tests for Floor Coverings

MEAN DISTANCE OF FLAME TRAVEL = 90mm

AVERAGE CRITICAL RADIANT FLUX = $\geq 11\text{kW/m}^2$

AVERAGE INTEGRATED SMOKE VALUE = 47% x min

DTAC PTY LTD
ABN 41 093 070 127

Unit 4, 11-12 Phillip Court
Port Melbourne Victoria
Australia 3207

PO Box 5059
South Melbourne Victoria
Australia 3205

T 1300 793 478
F 1300 780 628


estimating@dtac.com.au
www.dtac.com.au

© DTAC Pty Ltd 2020

TACTILE CLASSIC YELLOW

INSTALLATION & APPLICATION

SUBSTRATE Stone / Masonry / Timber / Vinyl




CODE DT0600Y

FIXING Drill and pressure fit
(M8 x 25mm hole)

NOTE *Any thick substrate
where maximum hold is
required without chemical
anchoring*

SUBSTRATE Vitrified Porcelain / Ceramics / Glass / Metals



CODE DT0600Y

FIXING Diamond core/pressure fit
(M8 x 25mm hole)

NOTE *Any thick or thin non
drillable substrate*