


PEMKO® EDGING URBAN

MILL FINISHED ALUMINIUM



TYPE	Edging	
RANGE	Designer Stair Edging	
DESIGN	Urban	
MATERIAL	6063 T5 extruded aluminium alloy with silicon carbide infill	
FINISH	Mill Finished	



FEATURES

Intermittent striations of hard wearing, solid silicon carbide inserted into aluminium extrusions designed by DTAC in Australia

Available in exclusive premium quality flat or angle profiles

Suitable for all stable finished outdoor or indoor surfaces and substrates

 ${\tt Complies \ with \ Disability \ (Access \ to \ Premises-Buildings) \ Standards \ to \ meet \ the \ deemed-to-satisfy-provisions}}$

Complies with slip resistance requirements as detailed in HB 198

Backed by 2 year warranty

SLIP RESISTANCE TESTING

Important information: To determine a classification of a slip resistance rating, see Australian Standards Hand Book 198 (HB 198), a Guide to the specification and testing of slip resistance of pedestrian surfaces. This document outlines the minimum ratings of a location and situation of a pedestrian surface.

TEST	AS 4586 APPENDIX A: Wet Pendulum Test
FOUR S 96 SLIDER	= 77 CLASS = P5
TEST	AS 4586 APPENDIX B: Dry Floor Friction Test
MEAN COF	= 0.75 CLASS = D1
TEST	AS 4586 APPENDIX C: Wet/Barefoot Ramp Test
MEAN ANGLE OF INCL	NATION = 37° CLASS = C
TEST	AS 4586 APPENDIX D: Oil/Wet Ramp Test

LUMINANCE TESTING

Important information: To determine a luminance contrast between a substrate and the DTAC EDGING, see: AS 1428.1:2009. DTAC can test your substrate for luminance contrast to give you peace of mind that your DTAC project will be fully compliant to AS 1428.1 Appendix B.

TEST	AS 1428.1 APPENDIX B PARAGRAPH B3	
BLACK		
LUMINANCE REFLECT	ANCE RATING / WET	= 2.6
LUMINANCE REFLECTANCE RATING / DRY		= 3.6
YELLOW		
LUMINANCE REFLECT	ANCE RATING / WET	= 42.9
LUMINANCE REFLECTANCE RATING / DRY		= 45.0

FIRE TESTING

Important information: The results displayed in this document relate to the behaviour and environment of the product in the conditions to which the test was carried out. This is not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

TEST	AS/ISO 9239.1: Reaction to Fire T	ests for Floor Coverings
MEAN DIS	TANCE OF FLAME TRAVEL	= 5mm
AVERAGE	CRITICAL RADIANT FLUX	= ≥ 11kW/m2
AVERAGE	INTEGRATED SMOKE VALUE	= 2% x min

DTAC PTY LTD

ABN 41 093 070 127

Unit 4, 11-12 Phillip Court Port Melbourne Victoria Australia 3207

PO Box 5059 South Melbourne Victoria Australia 3205 PEMK0®

T 1300 793 478

estimating@dtac.com.au www.dtac.com.au

© DTAC Pty Ltd 2022





PEMKO® EDGING URBAN

FINISHES & SIZES

DESIGNER STAIR EDGING - AVAILABLE SIZES

MILL FINISHED








PEMKO® EDGING URBAN


INSTALLATION & APPLICATION

SUBSTRATE


Stone / Masonry / Timber / Vinyl




FIXING Adhesive. Optional screw-fix (colour matched screws and plugs supplied)



FIXING Adhesive. Optional screw-fix (colour matched screws and plugs supplied)




FIXING Adhesive. Optional screw-fix (colour matched screws and plugs supplied)




FIXING Adhesive. Optional screwfix (colour matched screws and plugs supplied*)

SUBSTRATE


Vitrified Porcelain / Ceramics / Glass / Metals



FIXING Adhesive. Optional screw-fix (colour matched screws and plugs supplied)



FIXING Adhesive. Optional screwfix (colour matched screws and plugs supplied)



FIXING Adhesive. Optional screw-fix (colour matched screws and plugs supplied)

NOTE Ensure grout line is discrete as illustrated



FIXING Adhesive. Optional screw-fix (colour matched screws and plugs supplied*)

NOTE Ensure grout line is discrete as illustrated

*Colour matched screws for DE0760MF only.