


# PEMKO® CORDUROY EDGING 10X50X3MM



### PRODUCT CODES: DESCRIPTION:

DE0110C	NATURAL ANODISED		
DE0110B	BLACK ANODISED		
DE0110G	GOLD ANODISED		
RANGE	Stair Nosing & Edging		
DESIGN	Corduroy		
MATERIAL	6063 T5 extruded aluminium alloy		
LOCATION	Indoor or outdoor		



### **FEATURES & BENEFITS**

Extruded continuous corduroy pattern designed by DTAC in Australia

Available in exclusive premium quality flat, angle or carpet profiles

Suitable for all stable finished indoor or outdoor surfaces and substrates

Complies with the NCC (D4D4 Parts of buildings to be accessible) where stated and Disability (Access to Premises—Buildings) Standards to meet the deemed-to-satisfy-provisions

Complies with slip resistance requirements as detailed in HB 198

Registered Australian design

### SLIP RESISTANCE TESTING

Important information: To determine a classification of a slip resistance rating, see Australian Standards Hand Book 198 (HB 198), a Guide to the specification and testing of slip resistance of pedestrian surfaces. This document outlines the minimum ratings of a location and situation of a pedestrian surface.

TEST	AS 4586 APPENDIX A: Wet Pendulum Test	
FOUR S 96 SLIDER	= 63 <b>CLASS</b> = P5	
TRL 55 SLIDER	= 66 <b>CLASS</b> = P5	
TEST	AS 4586 APPENDIX B: Dry Floor Friction Test	
MEAN COF	= 0.55 <b>CLASS</b> = D1	
TEST	AS 4586 APPENDIX C: Wet/Barefoot Ramp Test	
MEAN ANGLE OF INCL	- INATION = 33° CLASS = C	
TEST	AS 4586 APPENDIX D: Oil/Wet Ramp Test	
CORRECTED MEAN OV	ERALL ACCEPTANCE ANGLE = 31.7° CLASS = R13	

### **LUMINANCE TESTING**

Important information: To determine a luminance contrast between a substrate and the DTAC EDGING, see: AS 1428.1:2009.

TEST	AS 1428.1 APPENDIX B PARAGRAPH B3	
NATURAL		
LIGHT REFLECTANCE VALUE / WET		= 36.09
LIGHT REFLECTANCE VALUE / DRY		= 35.90
BLACK		
LIGHT REFLECTANCE	VALUE/WET	= 1.44
LIGHT REFLECTANCE VALUE / DRY		= 1.48
GOLD		
LIGHT REFLECTANCE VALUE / WET		= 31.32
LIGHT REFLECTANCE VALUE / DRY		= 32.34

**DTAC PTY LTD** ABN 41 093 070 127

Unit 4, 11-12 Phillip Court Port Melbourne Victoria Australia 3207 PO Box 5059 South Melbourne Victoria Australia 3205


PEMK0<sup>®</sup> T 1300 793 478 estimating@dtac.com.au dtac.com.au

© DTAC Pty Ltd 2025



## PEMKO® CORDUROY EDGING 10X50X3MM

FINISHES & SIZES






## PEMKO® CORDUROY EDGING 10X50X3MM

### INSTALLATION & APPLICATION

SUBSTRATE

Stone / Masonry / Timber / Vinyl



**CODE** DE0110C/DE0110B/DE0110G

**FIXING** Adhesive

SUBSTRATE

Vitrified Porcelain / Ceramics / Glass / Metals



**CODE** DE0110C / DE0110B / DE0110G

**FIXING** Adhesive

NOTE Ensure grout line is discrete as illustrated